

506
C1/


subjecting an oriented polyolefin material having a value of not exceeding 5×10^{-5} (1°C) for average coefficient of linear expansion in the $20 - 80^{\circ}\text{C}$ range to a heat treatment so that its surface melts; and
effecting joining of said oriented polyolefin material by the application of pressure and heat at a temperature below a melting point of the heat-treated oriented polyolefin material but sufficient to melt said surface.--

REMARKS

Claims 13-24 are pending in this application. These claims are directed to the subject matter of the binding process for a polyolefin article claimed in original claims 9 and 10. No new matter is contained in the amendments.

Please charge any fee deficiency or credit any overpayment to Deposit Account No. 01-2300.

Respectfully submitted,


George E. Oram, Jr.
Registration No. 27,931

Customer No. 004372
ARENT FOX KINTNER PLOTKIN & KAHN, PLLC
1050 Connecticut Avenue, N.W.
Suite 400
Washington, D.C. 20036-5339
Tel: (202) 857-6000
Fax: (202) 638-4810

GEO:ddd
38166_1.DOC